



# **Declaration of Performance**

# DoP no. 4 - 2mm painted

# 1. Unique identification code of the product type

Flue pipe named "2mm-painted"

# 2. Intended use

Connecting flue pipe from the appliance to the chimney.

# 3. Manufacturer

**SAVE S.r.I. Unipersonale** - Via Enrico Fermi, 16/A - I-36010 Chiuppano (VI) — Italy Tel. +39 0445 891068 - Fax +39 0445 891359 - save@savefumisteria.it

# 4. Representative

5. VVCP systems

Not applicable System 2+

#### 6a. Harmonised standard

EN 1856-2:2009

Notified body: **KIWA CERMET Italia Spa**, with identification number 0476, issued certificate No. **0476-CPR-7509** of conformity of the factory production control.

# **6b. European Assessment Document**

Not applicable

# 7. Declared performance

Diameters - mm	Reference Standard	Designation	Sealing Elastomers
120-125	EN 1856-2	T600-N1-W-Vm-L01200-G375NM	Not present
130-140-150	EN 1856-2	T600-N1-W-Vm-L01200-G450NM	Not present
160-180-200	EN 1856-2	T600-N1-W-Vm-L01200-G600NM	Not present

Essential characteristics	Performance	Harmonized technical specification
Total thickness after enamel-coating	2mm	
Compressive strength	NPD	
Fire resistance	Ø 120-125 G375NM Ø 130-140-150 G450NM Ø 160-180-200 G600NM	
Gas tightness	<b>N1</b> ( $\leq$ 2 ls <sup>-1</sup> m <sup>-2</sup> at 40 Pa)	
Roughness coefficient	0.1 mm (stated)	
Flow resistance D. 120 x 1000 D. 120 - 90° elbow D. 120 - 45° elbow	0,9 dp (Pa) at 6 m/s 7,9 dp (Pa) at 6 m/s 5,2 dp (Pa) at 6 m/s	EN 1856-2:2009
Thermal resistance	NPD	
Thermal shock resistance Sootfire resistance Temperature class	G - Test passed T600	
Flexural strength	NPD	<del></del>
Resistance to steam and/or condensate	W - Test passed	
Corrosion resistance	Class Vm	
Freeze/thaw resistance	NPD	





# 8. Appropriate technical documentation and/or specific technical documentation

See instructions for "2mm-painted" Model on following page.

The performance of the above-mentioned product complies with the combination of performances declared. This declaration of responsibility is issued pursuant to Regulation (EU) no. 305/2011 at the exclusive responsibility of the manufacturer above.

Chiuppano, 5 December 2024

Director

Vittorio Dalle Carbonare





# Instructions

# 2 mm painted

## Manufacturer

## SAVE S.r.I. Unipersonale

Via Enrico Fermi, 16/A - I-36010 Chiuppano (VI) – Italy Tel. +39 0445 891068 - Fax +39 0445 891359 save@savefumisteria.it

## Product designation in accordance with EN 1856-2:2009

Diameters - mm	Reference Standard	Designation	Sealing Elastomers
120-125	EN 1856-2	T600-N1-W-Vm-L01200-G375NM	Not present
130-140-150	EN 1856-2	T600-N1-W-Vm-L01200-G450NM	Not present
160-180-200	EN 1856-2	T600-N1-W-Vm-L01200-G600NM	Not present

### **Characteristics**

- Steel single wall connecting flue pipe externally coated with heat resistant silicon paint. Thickness of steel: 2 mm.
- Maximum operating temperature: 600°C.
- Suitable for operating with natural draught appliances also in wet conditions (in the presence of condensate) when installation is performed
  as described below.

## **Assembly instructions**

- 2mm-painted flue pipes are cylindrical with a taper at one end that serves as a socket to permit connection with other elements.
- Wet operation (when condensate is present inside the pipe): the pipes must be assembled in anti-condensate mode (with the female end of the pipe above and the socket below), in this way ensuring an upward slope of at least 3° in the non-vertical section.
- Minimum distance from combustible materials: see DoP no. 4.
- In non-vertical installations: fix every piece with a pipe holder.
- Before starting the operations, check the correct draught of flue system (connecting flue pipe + chimney).
- In any case, installation must be in accordance with the technical standards of the country.
- Avoid any tampering, cutting or other operations that could affect the validity of the properties declared in the DoP and therefore of the CE marking.

## Filling out the flue pipe plate



- 1 Tick the box indicating the line of product installed
- 2 Enter the designation of the line of product as shown in its DoP
- 3 Enter the diameter in mm
- 4 Enter the distance from combustible materials expressed as designated
- **5** Enter the name of the installer
- Enter the date of installation





# Cleaning

Connecting flue pipes must be periodically cleaned to ensure the stove has a suitable draught and operates well as a consequence.

Periodic cleaning also prevents the so-called sootfire, in other words the lighting of unburnt parts deposited inside the pipe.

The use of inspectable elbow connectors permits cleaning without requiring the disassembly of the parts: all you need to do is remove the inspection opening and then use a vacuum cleaner to suck up the soot from inside.

CLEANING INTERVAL: every 3 months of operation. Wherever long and especially horizontal sections are installed, cleaning should be performed more frequently.

# Inspection

The flue pipes must be checked periodically during the cleaning operations in order to ensure that they are in good conditions. In case of sootfire, an expert technician should inspect the flue system.

# **Storage instructions**

Avoid corrosive environments.